

Date received:

Date of test:

Date of issue:

Sample name:

**TEST REPORT** 

189615 / 1

22/01/15

22/01/15

26/03/15

Kicca ONE lava

CATAS S.p.A. Iscr. Reg. Imprese Udine nr. iscr. C.F. 01818850305 Reg. Impr. UD 20663 P. IVA : 01818850305 C.Soc. € 1.003.650,00 i.v.

Sede: Via Antica, 24/3 33048 S. Giovanni al Nat. UD Via Braille, 5 Tel. 0432.747211 r.a. Fax 0432.747250 http://www.catas.com e-mail: lab@catas.com

Filiale: 20851 Lissone MB Tel. 039.464567 Fax 039.464565 e-mail: lissone@catas.com

KASTEL S.R.L. VIA FRIULI, 35/37 31020 SAN VENDEMIANO (TV) ITALIA

## Artificial Weathering ASTM G 154-12

Apparatus used:	QUV spray
Lamps used:	UVB 313 nm
Irradiance:	0,71 W/mq
Irradiance determination system:	automatic
Cycle description:	4 hours UV at 60 ±3 °C black panel temperature
	4 hours condensation at 50 $\pm$ 3 °C black panel temperature

## Test results:

Exposure (hours)	Evaluation grey scale	Remarks
1.000	5	No chalking effect

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.

Managing Director Rr Andrea Giavon

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. pag. 1/1